

PV SEAL - FAST RECOVERY

Flexible Polyvinyl Chloride foam.

PROPERTY	UNIT	TEST METHOD	RANGE
APPARENT DENSITY: NOMINAL	kg / m ³		120
COMPRESSION STRESS-STRAIN CHARACTERISTICS: 40%	N	DIN 53576B	109.7
COMPRESSION-SET: 50 % rt / 72 hrs / 30 mins REC	%	DIN 53572	7.9
50 % rt / 72 hrs / 24 hrs REC	%	DIN 53572	1.1
DIMENSIONAL SHRINKAGE AFTER HEAT - TREATMENT (LENGTH DIRECTION): 4 hrs @ 60 °C	%		1.0
4 hrs @ - 30 °C	%		0.6
TENSILE STRENGTH:	kPa	DIN 53571	240
ELONGATION:	%	DIN 53571	137
FLAMMABILITY:	GRADE	FMVSS 302	Pass

MAXIMUM OPERATION TEMPERATURE:

The degree of shrinkage depends on the material type, density, temperature exposure time, part dimensions and cell size. Other temperatures may prove to be limiting, depending on the particular conditions of each application.

PLEASE NOTE:

The test methods applied in the above tests are DIN and FMVSS. The above results are obtained based on the referenced test methods and are to be regarded as typical values which are not usually directly comparable with those of any product tested to other test methods, i.e.: DIN. Tests were conducted at ambient temperature and humidity unless otherwise stated.

Whilst this document has been prepared in good faith, Sondor Industries (Pty) Ltd accept no contractual liability of any kind to any person in respect of its contents or any use made thereof, nor must it be assumed that any such use will not infringe any patent. This document shall form no part of any contract with a customer. The data supplied on this sheet is typical and in no way reflects the final resultant values of the respective products.



CAPE TOWN: Tel: (021) 959 9400, Fax: (021) 959 9434, E-mail: ctn@sondor.co.za **DURBAN:** Tel: (031) 705 4220, Fax: (031) 705 4566, E-mail: dbn@sondor.co.za **JOHANNESBURG:** Tel:(011) 452 4530, Fax: (011) 452 4532, E-mail: jhb@sondor.co.za
PORT ELIZABETH: Tel: (041) 486 2231, Fax: (041) 486 2234, E-mail: pe@sondor.co.za **PRETORIA:** Tel: (012) 803 4471, Fax: (012) 803 4400, E-mail: pta@sondor.co.za **EXPORTS:** Tel: +27-21-959 5900, Fax: +27-21-959 5901, E-mail: exports@sondor.co.za
HEAD OFFICE: Tel: (021) 959 5900, Fax: (021) 959 5901, E-mail: ho@sondor.co.za **EAST LONDON AGENT** – Jonny Grant 043 7433067/68
BLOEMFONTEIN AGENT – Build OFS 051 435 4880 **ZIMBABWE AGENT** - Security Devices/Leisure Lifestyle 00263 4 487064/5

WEB ADDRESS: www.sondor.co.za