DATA SHEET: ORTHOLITE FLESH

Date: Jul '24 Rev. No.: 2 Page: 1 of 1

The Ortholite product is the combination of cross-linked expanded EVA (Vinyl Acetate) and PE (Polyethylene) Foam. It is suitable for use in packaging, padding and footwear components. The Ortholite Flesh product range is free from CFC's and HCFC's.

PROPERTY	UNIT	TEST METHOD	NOMINAL (1)
DENSITY:	kg/m³	ISO 845	127
TENSILE STRENGTH: CD MD	kPa kPa	ISO 1798 ISO 1798	1527 1617
ELONGATION: CD MD	% %	ISO 1798 ISO 1798	312 338
COMPRESSION DEFLECTION: 10 % 25 % 50 %	kPa kPa kPa	ISO 3386 / 1 ISO 3386 / 1 ISO 3386 / 1	188 213 310
SHORE HARDNESS:	A°	INTERNAL	36

1. NOMINAL:

Indicative average value.

2. **DENSITY**:

Based on 90 % net bun yield.

PLEASE NOTE:

The above results are obtained based on the referenced test methods and are to be regarded as typical values which are not usually directly comparable with those of any product tested to other test methods, i.e.: DIN. Tests were conducted at ambient temperature and humidity unless otherwise stated.

Whilst this document has been prepared in good faith, Sondor Industries (Pty) Ltd accept no contractual liability of any kind to any person in respect of its contents or any use made thereof, nor must it be assumed that any such use will not infringe any patent. This document shall form no part of any contract with a customer. The data supplied on this sheet is typical and in no way reflects the final resultant values of the respective products.







CAPE TOWN: Tel: (O21) 959 9400, E-mail: SondorCPT@sondor.co.za • DURBAN: Tel: (O31) 705 4220, E-mail: SondorDBN@sondor.co.za JOHANNESBURG: Tel: (O11) 452 4530, E-mail: SondorJHB@sondor.co.za • PORT ELIZABETH: Tel: (O41) 486 2231, E-mail: SondorPE@sondor.co.za PRETORIA: Tel: (O12) 803 4471, E-mail: SondorPTA@sondor.co.za • EXPORTS: Tel: +27-21-959 5900, E-mail: SondorEXPORTS@sondor.co.za HEAD OFFICE: Tel: (O21) 959 5900, E-mail: SondorHO@sondor.co.za • EAST LONDON AGENT: Johnny Grant (O43) 743 3067/68 GARDEN ROUTE AGENT: IMPI Wire (O44) 802 7300