DATA SHEET: PV SEAL - FAST RECOVERY

Date: Oct '21 Rev. No.: 4 Page: 1 of 1

Flexible Polyvinyl Chloride foam.

PROPERTY	UNIT	TEST METHOD	RANGE
APPARENT DENSITY: NOMINAL	kg/m³		120
COMPRESSION STRESS-STRAIN CHARACTERISTICS: 40%	N	DIN 53576B	109.7
COMPRESSION-SET: 50 % rt / 72 hrs / 30 mins REC 50 % rt / 72 hrs / 24 hrs REC	% %	DIN 53572 DIN 53572	7.9 1.1
DIMENSIONAL SHRINKAGE AFTER HEAT - TREATMENT (LENGTH DIRECTION): 1.0 4 hrs @ 60 °C % 1.0 4 hrs @ - 30 °C % 0.6			
TENSILE STRENGTH:	kPa	DIN 53571	240
ELONGATION:	%	DIN 53571	137
FLAMMABILITY:	GRADE	FMVSS 3O2	Pass

MAXIMUM OPERATION TEMPERATURE:

The degree of shrinkage depends on the material type, density, temperature exposure time, part dimensions and cell size. Other temperatures may prove to be limiting, depending on the particular conditions of each application.

PLEASE NOTE:

The test methods applied in the above tests are DIN and FMVSS. The above results are obtained based on the referenced test methods and are to be regarded as typical values which are not usually directly comparable with those of any product tested to other test methods, i.e.: DIN. Tests were conducted at ambient temperature and humidity unless otherwise stated.

Whilst this document has been prepared in good faith, Sondor Industries (Pty) Ltd accept no contractual liability of any kind to any person in respect of its contents or any use made thereof, nor must it be assumed that any such use will not infringe any patent. This document shall form no part of any contract with a customer. The data supplied on this sheet is typical and in no way reflects the final resultant values of the respective products.







CAPE TOWN: Tel: (O21) 959 94OO, E-mail: Ctn.Sondor@ecobat.com

JOHANNESBURG: Tel: (O11) 452 453O, E-mail: Jhb.Sondor@ecobat.com

PRETORIA: Tel: (O12) 803 4471, E-mail: Pta.Sondor@ecobat.com

HEAD OFFICE: Tel: (O21) 959 59OO, E-mail: Ho.Sondor@ecobat.com

**EAST LONDON AGENT: Johnny Grant (O43) 743 3O67/68 ** GARDEN ROUTE

AGENT: IMPI Wire (O44) 802 73OO