

JOINTEX

Lightweight, cross-linked, closed cell, expanded Polyethylene joint former with hinged temporary blocking piece.

sondor
PERFORMANCE FOAMS

Used as an expansion / contraction joint former.

ADVANTAGES


- Jointex has good compression qualities with good recovery capacity.
- Supplied with a hinged temporary blocking piece, leaving a clean, neat and perfectly sized groove providing a consistent depth channel for joint sealant.
- Supplied cut to size, eliminating wastage and cutting on site.
- The material is flexible and can be used around corners.
- Excellent resistance to chemicals.
- Is waterproof, does not disintegrate, rot or swell.
- No bond breaker required.

PHYSICAL PROPERTIES / TECHNICAL DATA

- Composition: Closed cell, cross-linked expanded Polyethylene.
- Density: 33 kg/m³ (nominal).
- Size: Available in various sizes and thicknesses according to requirements.
- Compression Deflection: 10 %: 36 kPa; 25 %: 61 kPa; 50 %: 143 kPa.
- Compression-Set: 25 % 22 hr COMP. / 24 hr REC.: <6 %; 50 % 22 hr COMP. / 24 hr REC.: <20 %.
- Resistance: Good resistance to dilute acids and alkalis.
- Flammability: <310 mm / min. on a 3 mm sample.
- Thermal Conductivity: 24 °C: 0.037 W/m.K.
- Temperature Range: Up to 90 °C.
- Tensile Strength: >163 kPa.
- Elongation and Break: >144 %.

Please Note: In conjunction with water retaining structures, Jointex must **NOT** be used where the water head is in excess of 3 metres. Use Aquajoint (SPX 120) for applications where the water head exceeds 3 metres and is not more than 15 metres.


(Continued overleaf)



DIRECTIONS FOR USE

- Ensure all concrete surfaces are free from base grit and dust.
- Apply glue in vertical strips ± 100 mm wide and 25 mm from the top to avoid the tear-off strip from sticking to the concrete face.
- Allow the glue to dry (according to manufacturer's instructions) and then stick Jointex onto the glued concrete face.
- Cast the next section of concrete as required. Take care not to let the wet concrete get behind Jointex as this will result in a wavy joint.
- When the joint sealant is about to be applied, simply peel the tear-off strip out of the formed joint, leaving an even groove of uniform depth for filling with sealant.

Whilst this document has been prepared in good faith, Sondor Industries (Pty) Ltd accept no contractual liability of any kind to any person in respect of its contents or any use made thereof, nor must it be assumed that any such use will not infringe any patent. This document shall form no part of any contract with a customer. The data supplied on this sheet is typical and in no way reflects the final resultant values of the respective products.



sondor
PERFORMANCE FOAMS



CAPE TOWN: Tel: (021) 959 9400, E-mail: SondorCPT@sondor.co.za • **DURBAN:** Tel: (031) 705 4220, E-mail: SondorDBN@sondor.co.za
JOHANNESBURG: Tel: (011) 452 4530, E-mail: SondorJHB@sondor.co.za • **PORT ELIZABETH:** Tel: (041) 486 2231, E-mail: SondorPE@sondor.co.za
PRETORIA: Tel: (012) 803 4471, E-mail: SondorPTA@sondor.co.za • **EXPORTS:** Tel: +27-21-959 5900, E-mail: SondorEXPORTS@sondor.co.za
HEAD OFFICE: Tel: (021) 959 5900, E-mail: SondorHO@sondor.co.za • **EAST LONDON AGENT:** Johnny Grant (043) 743 3067/68
GARDEN ROUTE AGENT: IMPI Wire (044) 802 7300

Revision No.: 10/2024

www.sondor.co.za