

ZIPLAG

Sondor pipe Insulation lagging is manufactured from non cross-linked flexible expanded polyethylene with quick locking system, and is used for pipe insulation in hot and cold liquid applications.

ADVANTAGES

Pipe Insulation lagging offers the following benefits:

- Fully closed-cell foam
- Helps maintain the core temperature of liquids over extended periods of time in hot and cold piping applications
- Effective solution to reducing electricity and energy costs
- Noticeably slows down the time water pipes take to freeze [external temperature dependent]
- Noticeably slows down the time water pipes take to cool down in hot water applications [solar & geyser etc.]
- Acoustic barrier to reduce noise in pipe applications
- Low thermal conductivity, vapor transmission & water absorption
- Non toxic & does not attract rodents
- Fully recyclable & environmental friendly
- Supplied in various diameters to meet your insulation requirements
- Flexible and easy to cut and install
- Supplied with quick zip lock closing system

PHYSICAL PROPERTIES/TECHNICAL DATA

Range / Specification

- | | |
|---|---------------------------|
| • Wall thickness in mm: | 10mm & 15mm |
| • Temperature Range: | +8Ooc to -4Ooc |
| • ΔThermal Conductivity Test Method SABS: | ASTM C518 |
| • R-Value: 10mm | *O.210m ² .K/W |
| • K-Value: 10mm | *O.049 W/m.K |
| • R-Value: 15mm | **O.3O2m ² K/W |
| • K-Value: 15mm | **O.O51 W/m.K |
| • R-Value: 20mm | *O.393m ² .K/W |
| • K-Value: 20mm | *O.052 W/m.K |
| • Supplied in 2m lengths | |

FLAMMABILITY CHARACTERISTICS

Self extinguishing based on Sondor's internal test methods.

Non cross-linked expanded polyethylene foams do not weather well over extended periods of time if exposed to direct UV light. It is recommended that the product should be covered or painted with a suitable PVA paint if exposed to direct UV light.

Alternatively, change to Sondor SPX material for superior performance in extended UV and weathering applications. No need for painting or covering the product as this is a cross linked expanded PE foam (Not supplied with quick zip lock closing system).

Whilst this document has been prepared in good faith, Sondor Industries (Pty) Ltd accept no contractual liability of any kind to any person in respect of its contents or any use made thereof, nor must it be assumed that any such use will not infringe any patent. This document shall form no part of any contract with a customer. The data supplied on this sheet is typical and in no way reflects the final resultant values of the respective products.



sondor
PERFORMANCE FOAMS



CAPE TOWN: Tel: (O21) 959 9400, E-mail: SondorCPT@sondor.co.za • DURBAN: Tel: (O31) 705 4220, E-mail: SondorDBN@sondor.co.za
 JOHANNESBURG: Tel: (O11) 452 4530, E-mail: SondorJHB@sondor.co.za • PORT ELIZABETH: Tel: (O41) 486 2231, E-mail: SondorPE@sondor.co.za
 PRETORIA: Tel: (O12) 803 4471, E-mail: SondorPTA@sondor.co.za • EXPORTS: Tel: +27-21-959 5900, E-mail: SondorEXPORTS@sondor.co.za
 HEAD OFFICE: Tel: (O21) 959 5900, E-mail: SondorHO@sondor.co.za • EAST LONDON AGENT: Johnny Grant (O43) 743 3067/68
 GARDEN ROUTE AGENT: IMPI Wire (O44) 802 7300

Revision No: 9/2024